# **TECHNICAL DATA SHEET**



# **BOPP Carton Box Sealing Tape 105**

#### **❖ PRODUCT APPLICATIONS**

- ✓ Automated and manual sealing medium weight carton
- √ General sealing performance



## **❖ PRODUCT STRUCTURE**

Total Thickness	45 μm	
Film	Biaxially Oriented Polypropylene	
Adhesive	Water Base Acrylic Adhesive	
Colour <sup>(1)</sup>	Clear and Tan	

<sup>&</sup>lt;sup>(1)</sup> Contact your VISKO sales representative for other available colour or customized matching colours.

## ❖ SIZE AVAILABILITY<sup>(2)</sup>

JUMBO ROLL	FINISHED ROLL			
1280mm (W) X 6000m (L)	STANDARD WIDTH, mm	36, 48, 60, 72		
1610mm (W) X 6000m (L)	STANDARD LENGTH, m	50, 80, 90, 100, 900, 1000		
<sup>(2)</sup> Contact your VISKO sales representative for other available sizes				

#### **❖ PHYSICAL PROPERTIES**

Test Item		Typical Result <sup>(4)</sup>	Testing method
Total Thickness <sup>(3)</sup> (µm)		45	PSTC 133
180° Peel Adhesion, (gf/25mm)		585	PSTC 101
Holding Power (Hours)		72	PSTC 107
Initial Ball Tack (mm)		25	PSTC 6
Tensile Strength,	MD	12.8	DCTC 121
(kg/mm <sup>2</sup> )	TD	20.0	PSTC 131
Elongation at Break, (%)		125	PSTC 131

<sup>(3)</sup> Total thickness allowance ±1μm

## **❖ STORAGE CONDITION**

The tape should be stored in its original packaging in a cool, dry area and away from direct sunlight, temperature at 5-26°C, Relative Humidity 40-60 %.

#### ♦ SHELFTIFF

To obtain best performance, use this product within 18 months from the date of manufacture.

# **❖ USAGE CONDITION**

Surfaces to which the tape is applied should be clean, dry and free of grease, oil or contaminants

# **Important Notice to Purchaser**

All properties are approximate and are based on tests believed to be reliable and performed in conformance with recommended test methods. These values are presented for comparison purposes and do not represent a guarantee by the manufacturer. It is suggested that purchasers should test, prior to use, the suitability of this product for their particular application.

<sup>&</sup>lt;sup>(4)</sup> The typical result were collected from the average result of series of tests, it is not the product specification.